






COLORSOL® 凯乐素®		CLF				
		黄 CLF Yellow CLF	黄 NP Yellow NP	红 CLF Red CLF	蓝 CLF Blue CLF	蓝 NG Blue NG
漂白全棉布 Bleached 100% cotton						
染料/dyes	g/l	5	5	5	5	5
适用工艺 Suitability	冷轧堆染色 Cold Pad Batch	■	■	■	■	■
	轧干轧蒸染色 PDPS	■	■	■	■	■
	轧干焙烘染色 PDT	■	■	■	■	■
日晒牢度, 氙灯Xenon Light ISO 105-B02	1/25SD	4	5-6	5	5	5-6
	1/6SD	5	5-6	5-6	6	5-6
日晒牢度, 氙灯Xenon, 1/1SD Light AATCC16E	20AFU	4-5	4-5	4-5	4-5	5
	40AFU	4-5	4-5	4-5	4-5	5
水洗牢度 60 °C 1/1SD Washing ISO105-C06 C1S	CH	4-5	5	5	5	4-5
	CO	5	4-5	5	4-5	4-5
	CV	5	5	5	5	5
多次水洗牢度 60 °C 1/1SD Multiple Washing ISO 105-C06 C1S, 5X	CH	4-5	4-5	5	4-5	4-5
	CO	5	4-5	5	5	4
	CV	5	4-5	5	5	4-5
过氧化物水洗牢度95°C 1/1SD Peroxide washing ISO 105-C06 E2S	CH	4-5	4-5	5	4-5	4-5
	CO	5	4-5	5	4-5	4-5
	CV	5	5	5	4-5	5
水渍牢度 1/1SD Water ISO 105-E01	CH	5	5	5	5	4-5
	CO	5	4-5	5	5	4-5
	WO	5	5	5	5	5
汗渍牢度 酸性/碱性 1/1SD Perspiration acid / alkaline ISO 105-E04	CH	5/5	5/5	5/5	4-5/4-5	4-5/4-5
	CO	5/5	4-5/4	5/5	5/5	5/4-5
	WO	5/5	5/4-5	5/5	5/5	5/5
氯水牢度 1/1SD Chlorinated water ISO105-E03 20mg/l	CH	3-4	4-5	2-3	3-4W	4
氧化漂白牢度 1/1SD Oxidative bleach damage M&S C10A	CH	4-5	5	4-5	4	4-5
氧化氮牢度NOx 1/1SD ISO105-G01	1cycle CH	5	5	5	3-4GW	4-5
	3cycle CH	4-5	5	5	3GW	4-5