

COLORSOL® 凯乐素®	HLP		
	黄 Yellow HLP	红 Red HLP	蓝 Blue HLP

漂白全棉布
Ble ached 100% cotton



染色浓度 Dyeing concentration	%	0.5	0.5	0.5
适用工艺 中温浸染Warm Exh Dyeing		■	■	■
Suitability 涤棉浸染PE/CO Exh Dyeing		■	■	■
日晒牢度，氙灯Xenon Light AATCC16E	1/25SD	5	4	4-5
	1/6SD	5	4	4-5
日晒牢度，氙灯Xenon,1/6SD Light AATCC16E	20AFU	4-5	4	4-5
	40AFU	4-5	4	4-5
水涤牢度 60 ° C 1/6SD Washing ISO105-C06 C1S	CH	4-5	4-5	4-5
	CO	5	4-5	4-5
	CV	5	4-5	4-5
多次水涤牢度 60 ° C 1/6SD Multiple Washing ISO 105-C06 C1S,5X	CH	4-5	4-5	4-5
	CO	4-5	4	4-5
	CV	4-5	4-5	4-5
过氧化物水涤牢度 95 ° C 1/6SD Peroxide washing ISO 105-C06 E2S	CH	4-5	5	5
	CO	4-5	5	5
	CV	4-5	5	5
水渍牢度1/6SD Water ISO 105-E01	CH	4-5	4-5	4-5
	CO	4-5	4-5	4-5
	WO	4-5	4-5	4-5
汗渍牢度 酸性/碱性1/6SD Perspiration acid / alkaline ISO 105-E04	CH	4-5/4-5	4-5/4-5	4-5/4-5
	CO	5/5	5/5	5/5
	WO	5/5	5/5	5/5
氯水牢度1/6SD Chlorinated water ISO105-E03 20mg/l	CH	4-5	2	2
氧化漂白牢度1/6SD Oxidative bleach damage M&S C10A	CH	4-5	4-5	4-5
氧化氮牢度NOx 1/6SD ISO105-G01	1cycle CH	5	5	3-4GW
	3cycle CH	5	5	3-4GDu