

COLORSOL® MF 凯乐素® MF		黄 MF Yellow MF	红 MF Red MF	蓝 MF Blue MF	黄 MF-2R Yellow MF-2R	黄 NP Yellow NP	红 MF-3GL Red MF-3GL	红 MF-R Red MF-R	红 MF-2BL Red MF-2BL	深红 MF-D Deep Red MF-D	蓝 MF-R Bril Blue MF-R	蓝 4R Bril Blue 4R	蓝 MF-R Blue MF-R	蓝 NG Blue NG	藏青 MF-R Navy MF-R	藏青 MF-G Navy MF-G
漂白全棉布 Bleached 100% cotton																
染色浓度 Dyeing concentration %		1.0	1.0	1.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	4.0	2.0	2.0	4.0	4.0
适用工艺 中温浸染 Warm Exh Dyeing		■	■	■	■	■	■	■	■	■	■	■	■	■	■	■
Suitability 涤纶浸染 PES/CO Exh Dyeing		■	■	■	■	■	■	■	■	■	■	■	■	■	■	■
日晒牢度, 氙灯 Xenon Light ISO 105-B02		1/1SD 5-6	4	5	5-6	6-7	5	4	5-6	5	5-6	6	7	7	4-5	3-4
		2/1SD 6	4-5	5-6	6	6-7	5	4-5	6	5-6	6	6	7	7	5-6	4
日晒牢度, 氙灯 Xenon 1/1SD Light AATCC16E		20ADU 4-5	4-5	4-5	4-5	4-5	4-5	4-5	5	5	5	4-5	4-5	5	3-4	5NL
		40ADU 4-5	4	4	4-5	4-5	4	4	4-5	4-5	5	4-5	4-5	5	3	4-5NL
水洗牢度 60°C 1/1SD Washing ISO 105-C06 C1S		CH 5	5	5	5	5	5	5	5	4-5	4-5	5	5	4-5	4-5	5
		CO 5	5	5	5	4-5	5	5	5	4-5	5	5	4-5	4-5	4-5	5
		CV 5	5	5	5	5	5	5	5	4-5	5	5	5	5	5	5
多次水洗牢度 60°C 1/1SD Multiple washing ISO 105-C06 C1S, 5X		CH 4-5	4-5	4-5	4-5	4-5	5	5	5	4	4	5	4-5	4-5	4-5	5
		CO 5	5	4-5	5	4-5	5	5	5	5	5	5	5	4	4-5	5
		CV 5	5	5	5	4-5	5	5	5	5	5	5	5	4-5	5	5
过氧化物水洗牢度 95°C 1/1SD Peroxide washing ISO 105-C06 E2S		CH 4-5	4-5	4-5	5	4-5	5	5	5	4-5	4-5	5	4-5	4-5	4-5	5
		CO 4-5	4-5	4-5	5	4-5	5	5	5	4	4	5	4-5	4-5	4	4-5
		CV 4-5	4-5	4-5	5	5	5	5	5	4-5	5	5	4-5	4-5	4-5	5
水渍牢度 1/1SD Water IOS 105-E01		CH 4-5	4-5	4-5	5	5	4-5	5	5	5	4	5	5	4-5	5	5
		CO 5	5	5	5	4-5	5	4-5	5	4-5	5	5	5	4-5	5	5
		WO 5	5	5	5	5	5	4-5	5	5	4-5	5	5	5	5	5
汗渍牢度 酸性/碱性 1/1SD Perspiration acid / alkaline ISO 105-E04		CH 5/5	4-5/4-5	4-5/4-5	4-5/4-5	5/5	4-5/4-5	5/4	5/5	5/4-5	4/4	5/5	4-5/4-5	4-5/4-5	5/5	5/5
		CO 5/5	5/5	5/5	5/5	4-5/4	5/5	4-5/4-5	5/5	4-5/5	4/4	5/5	5/5	5/4-5	5/5	5/5
		WO 5/5	5/5	5/5	5/5	5/4-5	5/5	5/5	5/5	5/5	4-5/4-5	5/5	5/5	5-5	5/5	5/5
氯水牢度 1/1SD Chlorinated water ISO105-E03 20mg/l		CH 4	4-5	3-4	4	4-5	5	5	2-3	4-5	2	2GW	3-4W	4	2/3	4-5
氧化漂白牢度 1/1SD Oxidative bleach damage M&S C10A		CH 4-5	4-5	5	4-5	5	4	4	4-5	4-5	4-5	4-5	4	4-5	4-5	5
氧化蓝色牢度 NOx 1/1SD ISO105-G01		1cycle CH 5	5	4	5	5	5	5	5	5	4	3-4	3-4GW	4-5	5	5
		3cycle CH 5	4-5	3-4	5	5	5	5	5	5	3-4	2-3	3GDu	4-5	4-5	5

相关用语/Key

色牢度 Fastness	CH	色变 Shade change	Du	较暗 Duller	W	较浅 Weaker	G	较绿 Greener	CO	棉沾色 Staining of cotton	CV	粘胶沾色 Staining of viscose	WO	羊毛沾色 Staining of wool	SD	标准深度 Standard depth	NL	浅藏青 Light navy	AFU	AATCC褪色单位 AATCC fading unit	cycle	周期 cycle
-----------------	----	--------------------	----	--------------	---	--------------	---	---------------	----	---------------------------	----	-----------------------------	----	--------------------------	----	------------------------	----	-------------------	-----	--------------------------------	-------	-------------

敏感性
Sensitivity

■	无敏感性, 高度推荐 Not sensitive
■	稍敏感, 推荐 Slightly sensitive
■	中等敏感, 有局限性 Moderately sensitive
—	高度敏感, 不推荐 Highly sensitive